









Doc. Nr. TDS_1-825

Version: 2024_01

2K HS ALLCLEAR
1-825

Eurolux 2K HS All Clear 1-825 has a deep and rich gloss with outstanding levelling and structure. Non-yellowing and excellent chemical and mechanical properties. Strong UV-protection. Suitable for car and truck repair. Air drying and forced drying. Provides a long-term surface protection and has excellent adhesion and optimal flow on solvent borne and waterborne basecoats. Only for professional use.

	Mixing ratio (by volume), at 20°C	100% 2K HS All Clear 1-825 50% 2K HS Hardener 2-825 Std / 2-826 Fast 0 - 5% 2K Thinner 3-50 Std / 3-51 Fast
	Potlife	1 hr
	Sprayviscosity, DIN 4, at 20°C	17 – 20 s
	Application method	1,3 – 1,4 mm 2,0 – 2,5 bar
	Number of spraycoats	2; Film thickness 40 – 60 µm
	Flash off at 20°C	5 - 10 min
	Drying time at 20°C: 60°C:	12 hr 30 min
	Theoretical coverage	11 - 12 m ² /l (50 µm dry film thickness)
	VOC-regulation	VOC-compliant 2004/42/II B(e)(840)550
	Storage	Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place. Storage temperature above 3°C.
	Shelf-life	4 years

The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.