









Doc. Nr. TDS_6-016

Version: 2024_01

LIGHT PUTTY 6-016

Eurolux Light Putty 6-016 is a universal light putty with a very fine grain. Due to the low density it's very easy to spread. Easy to apply, fast drying and process with coarse and fine sanding paper. Good adhesion to steel, galvanized steel, aluminium, polyester laminates and old paint layers. It has good flexibility and adhesion on both primed and unprimed surfaces. Very smooth sanding. Only for professional use.

| | | |
|---|--|---|
|  | Surface preparation | Degrease, abrade and clear the surface |
|  | Surface preparation | Degrease again and dry thoroughly |
|  | Mixing ratio (by weight), at 20°C | 100% Light Putty 6-016 2 - 3% Curing agent Mix thoroughly 100 parts by weight of the putty with 2 - 3 parts by weight of the curing agent until a uniform colour is obtained. Using too much hardener can result in discolouration of the topcoat. |
|  | Application | Apply the putty in thin layers within 4 - 5 minutes / 20°C from mixing the curing agent. Applying temperature should be at least 10°C. |
|  | Drying time at 20°C: | 20 – 30 min |
|  | Sanding | Course sanding should be done with sandpaper P80 – P120 Finishing sanding should be done with sandpaper P120 – P240 |
| | VOC-regulation | VOC-compliant Max VOC content in ready to use product 250 g/l |
| | Storage | Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place. Storage temperature above 3°C. |
| | Shelf-life | 2 years |

The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.